## prototypeprojects

3D MADE, SIMPLE,®

## PROTOTYPE PROJECTS MATERIAL GUIDE Micro 3D Printing

## **Matrix HTL**

A high performance engineering material used for Micro 3D printing

Matrix HTL is a high performance engineering material with high strength, rigidity, and heat resistance, able to withstand temperatures up to 140C. Matrix HTL enables high resolution features, making it suitable for a broad range of engineering and medical applications including those which require autoclave sterilisation.

		Cured parts	Standard
Tensile Properties	Tensile Strength	71.5 MPa	ASTM D638
	Elastic Modulus	2397 MPa	ASTM D638
	Elongation at Break	7.8%	ASTM D638
Flexural Properties	Flexural Strength	112.9 MPa	ASTM D790
	Flexural Modulus	2.8 GPa	ASTM D790
Impact Properties	Impact Strength	30 J/m	ASTM D256
Thermal Properties	CTE @ 60C	169.0 μm/m/°C	-
	HDT @ 0.45 MPa	114.2 °C	ASTM D648 - 07
General properties	Contact Angle	45-60°	ASTM D7334
	Water Absorption (24h)	1.05%	ASTM D570
	Dialectic Constant (10 GHz)	3.45	-
	DF	0.0245	-
	Hardness	81 Shore D	ASTM D785
	Viscocity	85 cP	-
	Standard Colour	Black / Carbon black / Yellow	-

<sup>&</sup>lt;sup>1</sup> Final properties are dependent on print conditions, post-processing operations, and part geometry.

<sup>&</sup>lt;sup>2</sup> Test samples were UV cured and heat cured.





Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. Prototype Projects makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2025 by Prototype Projects Ltd. All rights reserved.